

Toll Free: 87 PERMATEX (877-376-2839)

6875 Parkland Boulevard, Solon Ohio 44139

Technical Data Sheet

Permatex® Water BondTM

AAM Revised 01/19

PRODUCT DESCRIPTION

Permatex® Water BondTM is a two part, hand kneadable, putty type industrial strength epoxy in stick form. Contrasting white and beige colored materials are mixed together to form a uniform off white color to indicate thorough mixing. After 1 hour, Water BondTM can be drilled, sanded, sawed, machined or painted and it is resistant to water and most solvents. Water BondTM is also NSF approved for use with repairs that are exposed to potable water. Permatex® Water BondTM does not bond to polyethylene and polypropylene and it is not intended for structural applications.

PRODUCT BENEFITS

- Easy to use
- No heating required
- 5 minute working time
- For interior and exterior use
- Can be applied to wet areas and cures underwater
- Safe for repairs that come in contact with drinking water
- Useable in 1 hour
- Good moisture resistance
- Withstands moderate temperatures
- Cured material will not shrink
- Non-flammable
- · Contains no solvents or VOC's

Bonds to most materials including:

- Fiberglass
- PVC and Most Plastics
- Metals including Aluminum, Steel, Iron, and Copper
- Concrete
- Ceramics
- Wood
- Water BondTM does not bond Polyethylene and Polypropylene Plastics

DIRECTIONS FOR USE

- Before starting, make sure your work area is protected from accidental spills. Surfaces must be clean, dry and free of grease and oil. Note: Wear impervious gloves when mixing or handling uncured Water BondTM.
- Roughen smooth surfaces to be repaired with sandpaper or mechanically.
- Cut off required amount of epoxy stick and knead with fingers to a uniform color. This should take no longer than two minutes. Note: Water Bond™ has a 3 to 5 minute working time (including mixing time).
- Apply to the surface to be repaired. Force into cracks or holes to be filled. Excess material can be removed, before it is cured, with a tool wetted with clean water.

- On wet or damp surfaces, work material into area forcefully and hold in place until adhesion begins. Do not use hands to hold in place as heat is given off during cure.
- 6. After 3 to 5 minutes, the epoxy will harden.
- After 1 hour, the cured material can be drilled, sanded, sawed, machined or painted. Product fully cures in 24 hours.

For Cleanup

- Cleanup must be completed before the product has cured. Use acetone or mineral spirits for project/tool cleanup.
- Clean hands with Permatex[®] Fast Orange[®] hand cleaners.

PROPERTIES OF UNCURED MATERIAL

Typical Value

Chemical Type
Appearance
Odor
Specific Gravity (mixed)
Flash Point, SCC, °F
Mix Ratio
Tensile Strength, steel

Typical Value
Epoxy and mercaptan resins white outside, beige inside
Slight mercaptan
1.90 g/ml
>200
1:1
900 psi

TYPICAL CURING PERFORMANCE

Permatex $^{\otimes}$ Water Bond $^{\text{TM}}$ has a working time of 3 to 5 minutes, functionally cures in 1 hour, and fully cures in 24 hours.

TYPICAL ENVIRONMENTAL RESISTANCE

Temperature Resistance
Continuous, °F Maximum
-40°F to 250°F
Intermittent, °F Maximum
-40°F to 300°F

Chemical / Solvent Resistance

This product retains effective properties when in contact with water, hydrocarbons, ketones, alcohols, esters, halocarbons, aqueous salt solutions, and dilute acids and bases.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as an adhesive for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
84331	2 oz. Water Bond TM
	with vial, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 46°F and 82°F (8°C and 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits. This product may be covered by one or more United States or foreign patents or patent applications.